

Promoting healthy communities

To the Director of Health Town of		Application/Permit #:		New \$175
To the Director of Health, Town of:		Date:		Repair \$100
Application is hereby made for an approval to construct a subsurface sewage disposal system for a:				
	(Residential Building, Resta	aurant, Retail Building, etc	c.)	
located at:(Street /	Address, Lot Number, Subdi	ivision Name, Map, Block	, Lot, etc.)	
New System:Addition:	Repair:	Other:		
Owner:	Address:		Tel.# _	
Installer:	Address:		Tel.#	
Installer License No In accordance with detailed informat		Sieve Source/Date:		
Application fee paid:Si				
Application ree paid3	(O)	wner and/or Licensed Ins		
		FORMATION		
Soil Tests Conducted (Date):		Lot size:	sq.ft.	
Area of Special Concern (Y/N)	If yes, Reason(s):			
Basis of Design (# of Bedrooms, Resta	urant Seats, Building Size, e	etc):		
Engineered Plan Required (Y/N):If	yes, Name of Engineer:		<u> </u>	
Address of Engineer:		Tel. #		
Design Plan Approved (Y/N):Da	ate of Approved Plan:	Revision D	Date:	
Type of Water Supply:	If well, has location b	peen approved (Y/N):		
Well Driller's Name:		T JSE ONLY	el. #	
Approval to Construct is hereby issued	(Print Nar	me)		





Connecticut Public Health Code Technical Standards for Approved Septic Fill, C 33 Sand and Stone Aggregate

Select fill is material placed within and adjacent to leaching system areas and comprised of clean bank run sand, clean bank run sand and gravel, or approved manufactured fill that is free from organic matter or foreign substances and having a gradation which conforms to the specifications stipulated in the current Technical Standards (see below) or ASTM C 33 (see below). Select fill shall meet the following requirements unless otherwise approved by the design engineer, however a design engineer cannot approve fill exceeding 6% passing the #200 wet sieve::

- 1. The select fill shall not contain any material larger than the three (3) inch sieve.
- 2. Up to 45% of the dry weight of the representative sample may be retained on the #4 sieve (This is the gravel portion of the sample).
- 3. The material that passes the #4 sieve is then <u>reweighed</u> and the sieve analysis started.
- 4. The remaining sample shall meet the following gradation criteria:

SELECT FILL SIEVE SIZE	PERCENT PASSING		
	WET SIEVE	DRY SIEVE	
#4	100	100	
#10	70 - 100	70 - 100	
#40	10 - 50 *	10 - 75	
#100	0 - 20	0 - 5	
#200	0 - 5	0 - 2.5	

C 33	PERCENT
SIEVE SIZE	PASSING
0.375″	100
#4	95.0-100
#8	80.0-100.0
#16	50.0-85.0
#30	25.0-60.0
#50	5.0-30.0
#100	< 10
#200	< 5

* Percent passing the #40 sieve can be increased to no greater than 75% if the percent passing the #100 sieve does not exceed 10% and the #200 sieve does not exceed 5%. If the fill fails the dry sieve but passes the wet sieve, then the fill shall be approved.

The licensed installer is responsible for preparing the leaching area with necessary select fill. The topsoil in the leaching system area must be removed and the subsoil scarified prior to select fill placement unless otherwise directed by the design engineer. The installer shall take the necessary steps to protect the underlying naturally occurring soil from over compaction or damage. Select fill shall extend a minimum of five (5) feet laterally in all directions beyond the outer perimeter of the leaching system and LLHD requires a current passing sieve (from the previous 30 days) be presented to the sanitarian or be on file with LLHD prior to placement of fill. LLHD may require a test of onsite material.

The Commissioner of Public Health must approve manufactured fill. Rock used to produce manufactured fill must have a loss of abrasion of not more than 50 % using AASHTO Method T-96. Suppliers of manufactured fill must make application for approval to the Commissioner of Public Health. Documentation must be submitted on the quarry operation, and production process. Fill specifications (gradation, permeability, etc) and a narrative of the quality control/quality

assurance program must also be included. The manufactured fill producers must provide annual product registrations to the Commissioner of Public Health.

Stone aggregate means crushed or broken stone, or crushed and uncrushed gravel meeting the gradation for No. 4 or No. 6 aggregate per Connecticut Department of Transportation Form 816 Specification M.01.01 (or latest specification) and the #40 and #200 sieve gradation stipulated above, based on the wet sieve analysis. Stone aggregate shall be free of silt, dirt or debris and shall show a loss of abrasion of not more than 50% using AASHTO Method T-96, and when tested for soundness using AASHTO Method T-104 not have a loss of more than 15% at the end of 5 cycles.

	No. 4 Stone Aggregate (AKA 1 & ¼" Stone)	No. 6 Stone Aggregate (AKA ¾" Stone)
SIEVE SIZE	PERCENT PASSING (by weight)	PERCENT PASSING (by weight)
2-inch	100	N/A
1.5-inch	90 - 100	N/A
1-inch	20 – 55	100
3/4-inch	0 - 15	90-100
1/2-inch	N/A	20-55
3/8-inch	0 – 5	0-15
#4	N/A	0-5
#40	0-3	0-3
#200	0-1.5	0-1.5